



G-FLOOR® ROLL-OUT FLOORING

Coin™, Diamond Tread™, Levant™, Ribbed™, and Small Coin™ Textures

DIVISION

09 65 00 Resilient Sheet Vinyl

PRODUCT DESCRIPTION

G-Floor® is a homogeneous polyvinyl floor covering that is waterproof, slip and stain resistant, mold and mildew resistant with a surface texture that can withstand high volumes of pedestrian traffic and is tough enough to drive a car on.

APPLICATIONS

Great for areas that call for a durable flooring solution. Garages, basements/recreational rooms, sheds, trailers, modular structures, commercial, retail and office environments, gyms, kennels, and more are all suitable applications for G-Floor® Roll-Out Flooring.

SUITABLE SUBSTRATES

Concrete (all grade levels), underlayment grade plywood and aluminum.

COMPOSITION

G-Floor® is composed of 100% polyvinyl and is 100% solid color. The top surface of the flooring is embossed with different surface textures that provide excellent slip resistance.

ASBESTOS AND LEAD FREE

STORAGE/INSTALLATION

Store all floor covering materials in a clean, dry environment with unused material on the core. Refer to Better Life Technology's installation manual.

LIMITED LIFETIME WARRANTY

• Standard Sizes

Thicknesses:

Coin	.075" base / .110" overall
Diamond Tread	.075" base / .130" overall
Levant	.055" base / .055" overall
Ribbed	.055" base / .120" overall
Small Coin	.060" base / .090" overall

Width: Up to 10'

Length: Up to 100'

• Typical Properties (.075).....ASTM Method

Specific Gravity, (+\ -0.02)....	1.32	D-792
Hardness, Shore A (+\ -3)....	0.85	D-2240
Tensile, PSI.....	2470	D-638
Elongation, %.....	330	D-638
100% Modulus, PSI.....	1200	D-412
Brittle Point, C.....	-24	D-746
Oxygen Index, %.....	0.23	D-2863
Tensile Retention, %.....	94.6	UL-1581
Elongation Retention, %.....	88.2	UL-1581

• Standard Colors:

Midnight Black, Sandstone or Slate Grey

• Oil Testing: On 7 Days in IRM 902 Oil @ 60 C, 0.075

• Residential Information: (ASTM F1914).. 250 psi 0.006..... Pass

• Statistic Load: (ASTM F970) 1000 psi 0.000..... Pass

• Coefficient of Friction: (ASTM C1028)

Coin™	Wet—1.04	Dry—1.00.....	Pass
Diamond Tread™	Wet—0.82	Dry—0.91.....	Pass
Levant™	Wet—0.89	Dry—0.97.....	Pass
Ribbed™	Wet—1.02	Dry—0.97.....	Pass
Small Coin™	Wet—0.82	Dry—0.92.....	Pass

• Critical Radiant Flux: (ASTM E648)

Class 1 per NFPA Life Safety Code 101 0.95 w/cm²..... Pass

• Abrasion Resistance: (ASTM D3389)

Net weight loss after 1000 revolutions:..... 0.30% Pass

• Smoke Density: (ASTM E662)..... Pass

• Flexibility: (ASTM F137)..... Pass

• Chemical Resistance: (ASTM F925)..... No Change..... Pass

• Fungi Resistance: (ASTM G21)..... Pass

• Federal Motor Vehicle Safety Standard #302:..... Pass

• GM 9070P Flammability Test: Does not Ignite (DNI) denotes that material does not support combustion during or after ignition.



Proudly manufactured in the USA.

BETTER LIFE TECHNOLOGY
9736 Legler Road, Lenexa, KS 66219

Toll-Free: 877-810-6444
www.blftlc.com